

Alkaline Zinc-Manganese Dry Battery Technology Specification

Customer _____

Part name Alkaline Zinc-Manganese Dry Battery

Model No Kiper Power Ultra Alkaline LR6/AA 1.5V

Serial No _____

Produce No _____

Approved by		Drafted by	Wenfei liang
Checked by		Signed by	Xiaojun nie
Prepared by		Valid Date	2026-06-15

Company address: Zapadnaya str., 7A, Minsk, 220004 Republic of Belarus

(Tel) : +375-29-337-14-14

E-mail: mail@kiper.by

Website: <https://www.kiper.by>

1 Scope

This specification defines the technical requirements for 1.5V LR6 Alkaline cells distributed by Pkcell. If not otherwise specified, the technical requirements and dimensions for cells should meet or exceed the requirements of GB/T 8897.1-2008, GB 8897.2-2008

2 Reference documents

GB8897.1-2008 (IEC60086-1:2000, IDT) Primary batteries-Part 1:General
 GB8897.2-2008 (IEC60086-2:2001, MOD) Primary batteries-Part 2:Physical and technological specifications
 GB8897.5-2006 (IEC 60086-5:2005, MOD) Primary batteries-Part 5:Safety of batteries with aqueous electrolyte

3 Chemical systems ,voltages and designation


3.1 Chemical systems:Alkaline manganese battery
 Zinc-Manganese dioxide

3.2 Nominal voltage:1.5V

3.3 Designation

IEC&GB(China): LR6; ANSI Number: AA;

4 LR6 Battery Dimensions



The	LR6	
Measure No	Max	Min
A	50.5	49.2
C	9.5	8.0
F	5.5	3.0
G	2.5	1.0
Ø	14.5	13.5

- 2 -

5 Voltage and Short current

Item	OCV (V)	CCV (V)	SCC (A)
Initial	$1.56 \leq OCV \leq 1.65$	≥ 1.45	≥ 6.0
After 12 months	≥ 1.56	≥ 1.4	≥ 5.0

OCV measurment:The inner resistance of Voltage Metre is above 1MΩ

C.C.V. measurment: After 0.2 ± 0.01 sec by $R=5.0 \Omega$

SCC measurment: $\pm 0.5\%$

6 LR6 discharge performance :

Discharge conditions				Average Minimum Discharge time
Load	Daily period	E. P. (V)	Initial	Delayed discharge performance after 12 months
3.9Ω	1h/d	0.8V	7.5h	7.2h
3.3Ω	4min/h, 8h/d	0.9V	330min	320min
24Ω	15s/m, 8h/d	1.0V	46.0h	45.0h
43Ω	4h/d	0.9V	92.0h	91.0h
1000mA	10s/m, 1h/d	0.9V	400time	370time
250mA	1h/d	0.9V	7.7h	7.4h
100mA	1h/d	0.9V	22.0h	21.0h
1500mW/2s 650mW/28	10T/h	1.05V	70time	60time
3.9Ω	24h	0.9V	380min	360min

- 3 -

Initial: 60 days after production

Test condition: $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$ and $60 \pm 15\% \text{RH}$

7 Leakage Resistance

Item	Test conditions	Sample size	Requirements	Acceptance
Overdischarge	10 Ω 24h/d for 48h at $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$,	n=9pcs	No leakage;Max of 0.35 mm height increase	Ac=0, Re=1
High Temperature and humidity storage	exposed to a temperature of $60^{\circ}\text{C} \pm 2^{\circ}\text{C}$ and RH90 $\pm$ 5% for a period of 3 weeks.	n=20pcs	No leakage	Ac=0, Re=1 - 4 -
45 $^{\circ}\text{C}$ Dry Storage	Stored for 12 weeks at 45 $^{\circ}\text{C}$	n=20pcs	No leakage	Ac=0, Re=1


8 Safety Requirement

Item	Test conditions	Sample size	Requirements of IEC60086-5:2005& GB8897.5-2006	Acceptance
------	-----------------	-------------	--	------------


Partial Use	Stored at $45^{\circ}\text{C} \pm 2^{\circ}\text{C}$ for 30days after undischarged batteries were test discharged 3.9Ω 24h/d, EPV=1.0V.	n=5pcs	No leakage;No explosion	Ac=0, Re=1
Thermal shock	See the following note 1, Total 10 Cycles	n=5pcs	No explosion	Ac=0, Re=1
Incorrect installation(3 + 1 anti-charge test)	Place three undischarged and unconditioned batteries in a series with one test sample battery reversed, Complete the circuit until vent activation or until the temperature of the reversed battery returns to ambient.	n=5pcs	No explosion	Ac=0, Re=1
Item	Test conditions	Sample size	Requirements of IEC60086-5:2005& GB8897.5-2006	Acceptance

Free fall	Drop each undischarged battery Two times, oriented in each of three mutually perpendicular face (six total) from a height 1 meter, onto a concrete surface, see the following note 2	n=5pcs	No explosion	Ac=0, Re=1
Overdischarge	Discharge one test sample battery(C1) with 43Ω resistance load until EPV is 0.6V, Connect three undischarged batteries and the sample battery in series with a 7.5Ω resistance load(R1) as shown in note 3, Maintain the circuit until the CCV of the series string reaches 1.2V	n=5pcs	No explosion	- 6 - Ac=0, Re=1

Note 1: Thermal shock



Note 2: Free fall



9 Inspection rules

10.1 Deliver inspection: Depending on GB2828

Number	Test	Item	IL	AQL
1	Dimensions	5	S-2	0.4
2	Appearance	--	II	1.0
3	Discharge capacity	7	--	--
4	Open-circuit voltage	4.5	II	1.0

Routine inspection: Depending on GB2829 and QB/T2389

10 Inspection for service output:

10.1 9 samples shall be tested for service output

- 7 -

10.2 If the average value is equal to or more than the value of table 1, and if the number of batteries showing a value less than 80% of the value of table 1 is 1 or less. The batteries are considered to conform to the requirement.

10.3 If the average value is less than the value of table 1, or if the number of batteries

showing a value less than 80% is 2 or more, the test shall be repeated with other 9 pieces. At the second test, if the average value is equal to or more than the value of table 1, and if the number of batteries showing a value less than 80% of the value of table 1 is 1 or less, these batteries are considered to conform to the requirement.

10.4 At above second test, if the average value is less than the value of table 1, or if the number of batteries showing a value less than 80% of the value of table 1 is 2 or more, the batteries are

considered not to conform to the requirement. third test shall not be performed.

11 Instructions for use

- 11.1 Always select correct size and grade of battery most suitable for intended use.
- 11.2 Replace all batteries of a set at the same time
- 11.3 Clean the battery contacts and also those of the equipment prior to battery installation
- 11.4 Ensure that batteries are installed correctly with regard polarity(+ and -);
- 11.5 Remove batteries from equipment which is not be used for an extended period of time;
- 11.6 Remove exhausted batteries promptly..

12. Display and storage

- 12.1 Batteries shall be stored in well-ventilated dry and cool conditions
- 12.2 Battery cartons should not be piled up in several layers, or should not exceed a specified height;
- 12.3 Batteries should not be exposed to direct sun ray for a long time or placed in areas where they get wet by rain. ;
- 12.4 Do not mix unpacked batteries so as to avoid mechanical damage and/or short circuit among each other

- 8 -


13 Storage life

Storage life of batteries are ten years long at $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$ and RH $60 \pm 15\%$

14 Marks

- 15.1 Designation;
- 15.2 Polarity of terminals;
- 15.3 Nominal voltage;
- 15.4 Mercury content;
- 15.5 Name or trade mark , manufacturer or supplier ;
- 15.6 Cautionary advice

Schematic diagram of discharge:



discharge Load: $3.9\ \Omega$

- 9 -

.....END.....